

Applications


welding stainless steels of AISI 301, 302, 304 & 308 composition. For welding of household articles, milk & soap industries. Hospital apparatus, apparatus for nitric acid, acetic acid.

Characteristics on Usage

This is a normal carbon 19/9 stainless steel electrode with a controlled ferrite content of 3 to 7 % for maximum resistance to cracking, corrosion and high temperatures upto 800 Degrees centigrade. The metal has excellent creep strength and is of radiographic quality.

Notes On Usage

- 1) Keep the arc as short as possible.
- 2) Remove dirt such as oil and dust from the groove.
- 3) Dry the electrode at 350°C for 60 Min- before use .

Welding Positions**Chemical Composition Of Weld Metal**

C%	Mn%	Si%	S%	P%	Cr %	Ni %	Mo %
0.080 Max	0.50- 2.50	1.00 Max	0.030 Max	0.040 Max	18.0 - 21.0	9.0 – 11.0	0.75 Max

Mechanical Properties Of Weld Metal

U.T.S. (N/mm ²)	ELONGATION (L = 5d)	Reduction Area %	FERRITE %.
550 Min	35 % Min	50 – 70	3.0 – 8.0 %

Approvals

P.D.I.L., E.I.L., TOYO[TEIL] ,RDSO ,IBR

Packing and Welding Current

SIZE (mm)	KG PER PACKET	KG PER CARTON	Current (Amps)	In Amps
2.50 x 350	2	10	AC 70 OCV / DC (+)	45 – 85
3.15 x 350	2	10		85 – 115
4.00 x 350	2	10		100 – 140
5.00 x 350	2	10		140 – 180

Packing

Vaccum packing